P.S. ELECTRIC - EASYWEED™ ELECTRIC

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	90 microns	Adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 084270.O CENTROCOT VEGANOK AZIENDA N. 1004

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	45°	60 gf	20 cm/sec	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	hot/cold

- → **Mirror cut the design**
- → **Weed excess material**
- → **Place the design on the garment**
- → **Heat apply at the conditions shown above**
- → **Peel carrier hot/cold**

PRODUCT HIGHLIGHTS

- → **reduced thickness**
- → **peralescent finish**
- → **bright colors**

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → **Wait 24 hours after the application before the first wash**
- → **Respect the textile recommendations**
- → **Do not bleach or use aggressive chemical agents**

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it

Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246